



检测报告

(Test Report)

No. BPQ11OEF95856541

样品名称
(Sample Description)

YBW3906 水性双组份清底漆
(YBW3906 Water-borne Varnish base-coat)

委托单位
(Applicant)

天津市裕北涂料有限公司
(Tianjin Yubei Paint Co.,Ltd)



检测结果 (Test Results)

No. BPQ11OEF95856541

第 1 页, 共 3 页 (page 1 of 3)

样品名称 (Sample Description)	YBW3906 水性双组份清底漆 (YBW3906 Water-borne Varnish base-coat)	样品数量 (Number of Samples)	清底漆(Varnish base-coat): 1kg 固化剂(Hardener): 200g
委托单位 (Applicant)	天津市裕北涂料有限公司 (Tianjin Yubei Paint Co.,Ltd)	样品等级 (Samples Rating)	—
规格型号 (Specification Model)	YBW3906	样品描述 (Sample Status)	无异常 (No Abnormality)
商 标 (Trade Mark)	伯丁克 BERDINGK	生产日期或批号 (Manufacturing Date or Lot No.)	2021 年 03 月 12 日/5C7C2W
到样日期 (Received Date)	2021-04-06	检测类别 (Test Type)	委托检测 (Commissioning Test)
检测日期 (Test Date)	2021-04-06~2021-04-12	检测环境 (Test Environment)	符合要求 (To meet the requirements)
样品来源 (Sample Source)	送样(Send Sample)		
检测项目 (Test Items)	见下页(See next page)		
检测方法 (Test Methods)	GB 18581-2020, GB/T 23986-2009, GB/T 23993-2009, GB/T 23990-2009, GB/T 31414-2015		
所用主要仪器 (Main Instruments)	气相色谱-质谱联用仪(GC-MS), 紫外-可见分光光度计(UV-Vis), 气相色谱仪(GC), 液相色谱仪(HPLC)		
备注 (Note)	1、YBW3906 水性双组份清底漆: 固化剂 WA501B: 水=5:1:0.8-1.5; (YBW3906 Water-borne Varnish base-coat: Hardener WA501B: Water=5:1:0.8-1.5); 2、限值标准: GB 18581-2020 表 1 水性涂料清漆。 (Limit Standard: GB 18581-2020 Table 1 Waterborne paint varnish).		
	编制人 (Edited by)	周燕	
	审核人 (Checked by)	陈淑娟	
	批准人 (Approved by)	杨明	
	签发日期 (Issued Date)	2021-04-14	

检测结果 (Test Results)

No. BPQ11OEF95856541

第 2 页, 共 3 页 (page 2 of 3)

样品名称和编号 (Sample Description and Number)	检测项目 (Test Items)	限值 (Limit)	检测结果 (Test Results)	单项结论 (Evaluation)
F95856541 YBW3906 水性双组份清底漆 (YBW3906 Water-borne Varnish base-coat)	VOC 含量 (Volatile Organic Compounds Content), g/L	≤300	32	符合 (Qualified)
	甲醛含量 (Formaldehyde content), mg/kg	≤100	未检出 (Not Detected) (<5)	符合 (Qualified)
	乙二醇醚及醚酯总和含量 (限乙二醇甲醚、乙二醇甲醚醋酸酯、乙 二醇乙醚、乙二醇乙醚醋酸酯、乙二醇二 甲醚、乙二醇二乙醚、二乙二醇二甲醚、 三乙二醇二甲醚) (Total content of Glycol Ether and Ether Ester (Limited to ethylene glycol methyl ether, ethylene glycol methyl ether acetate, ethylene glycol ethyl ether, ethylene glycol ethyl ether acetate, ethylene glycol dimethyl ether, ethylene glycol diethyl ether, diethylene glycol dimethyl ether, triethyl glycol dimethyl ether)), mg/kg	≤300	未检出 (Not Detected) (<20)	符合 (Qualified)
	苯系物总和含量 [限苯、甲苯、二甲苯(含乙苯)] (Total content of Benzene Series [Limited to benzene, toluene, xylene (including ethylbenzene)]), mg/kg	≤250	未检出 (Not Detected) (<20)	符合 (Qualified)
	烷基酚聚氧乙烯醚总和含量 { 限辛基酚聚氧乙烯醚 [$C_8H_{17}-C_6H_4-$ (OC_2H_4) $_n$ OH, 简称 OP_nEO] 和壬基酚聚氧 乙烯醚 [$C_9H_{19}-C_6H_4-$ (OC_2H_4) $_n$ OH, 简称 NP_nEO], $n=2\sim16$ } (Total content of alkylphenol polyoxyethylene ether { Octylphenol polyoxyethylene ether [$C_8H_{17}-C_6H_4-$ (OC_2H_4) $_n$ OH, abbreviated as OP_nEO] and nonylphenol polyoxyethylene ether [$C_9H_{19}-C_6H_4-$ (OC_2H_4) $_n$ OH, abbreviated as NP_nEO], $n=2\sim16$)), mg/kg	≤1000	未检出 (Not Detected) (<5)	符合 (Qualified)

—— 本页以下空白 ——


(The page below is blank)

检测结果 (Test Results)

No. BPQ11OEF95856541

第 3 页, 共 3 页 (page 3 of 3)

样品编号和照片(Sample Number and Photo):



仅对报告照片中的样品负责
(Pony authenticate the photo on original report only)

——以下空白——

(End of Report)

